




<b>TEST REPORT</b> <b>UN38.3, Sixth Edition</b> <b>Recommendations on transport of dangerous goods, manual of test and criteria,</b> <b>Section 38.3 - Lithium metal and lithium ion Batteries</b>	
Report Reference No.....	18PNS060075 03001
Date of issue.....	July 03, 2018
Total number of pages.....	13 pages
Testing Laboratory..... 检测单位	<b>GUANGDONG UTL CO., LTD.</b> 广东联鼎检测科技有限公司
Address..... 地址	Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China 东莞市南城街道雅园工业区中心路18号联鼎检测大厦
Tested by (name + signature).....	傅玲娟 
Reviewed by (name + signature).....	吴顺娣
Approved by (name + signature).....	吴娟
Applicant's name..... 申请者:	Shida Battery Technology Co., Ltd. 佛山市实达科技有限公司
Address..... 地址:	30 Xingye Road, Shishan Industrial Park, Nanhai District, Foshan City, Guangdong, P.R. China. 佛山市南海区狮山科技工业园C区兴业路30号
Manufacturer's name..... 制造商	Shida Battery Technology Co., Ltd. 佛山市实达科技有限公司
Address..... 地址	30 Xingye Road, Shishan Industrial Park, Nanhai District, Foshan City, Guangdong, P.R. China. 佛山市南海区狮山科技工业园C区兴业路30号
Factory's name..... 生产厂	Shida Battery Technology Co., Ltd. 佛山市实达科技有限公司
Address..... 地址	30 Xingye Road, Shishan Industrial Park, Nanhai District, Foshan City, Guangdong, P.R. China. 佛山市南海区狮山科技工业园C区兴业路30号
<b>Test specification/测试规范</b>	
Standard.....	ST/SG/AC.10/11/Rev.6/Section 38.3
Test procedure.....	N/A
Non-standard test method.....	N/A
<b>Test item description/样品名称.....</b>	
Trade Mark/商标.....	N/A
Model/Type reference/型号.....	XM6242125
Ratings..... 规格	14.8V, 4000mAh, 59.20Wh

**List of Attachments (including a total number of pages in each attachment):**

附件清单（含每个附件的总页数）：

- Photos documentation (2 pages)
- 产品图片 (2页)

**Summary of testing:**

测试信息概要：

**Tests performed (name of test and test clause):**

测试项目（测试命名及条款）

Test(s) 测试项目	Sample Number 样品编号
T.1: Altitude simulation / 高度模拟	b1# - b8#
T.2: Thermal test / 温度试验	
T.3: Vibration / 振动	
T.4: Shock / 冲击	
T.5: External short circuit / 外部短路	
T.6: Crush / 挤压	c1# - c5#
T.7: Overcharge / 过充电	b1# - b8#
T.8: Forced discharge / 强制放电	c6# - c25#

**Testing location:**

测试地点：

All tests as described in Test Case and Measurement Sections were performed at the laboratory described on page 1.  
所有测试项目均在第一页中测试单位实验室中进行。

The sample's status is good.

样品状况良好。

The conditions of the batteries of samples No. b1# to b4# are after first cycle ending in fully charged states.

样品编号b1# -b4#为第一次循环充放电周期后完全充电状态的电池。

The conditions of the batteries of samples No. b5# to b8# are after fifty cycles ending in fully charged states.

样品编号b5# -b8#为五十次循环充放电周期后完全充电状态的电池。

The conditions of the cells of samples No. c1# to c5# are at first cycle at 50% of the design rated capacity.

样品编号c1# -c5#为第一次循环充放电周期充电至标称容量的50%状态的电芯。

The conditions of the cells of samples No. c6# to c15# are at first cycle, in fully discharged states.

样品编号c6# -c15#为第一次循环充放电周期完全放电状态的电芯。

The conditions of the cells of samples No. c16# to c25# are after fifty cycles ending in fully discharged states.

样品编号c16# -c25#为五十次循环充放电周期后完全放电状态的电芯。

GUANGDONG UTL CO., LTD.

Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China

Tel:+86-769-3893 3228 Fax:+86-769-3893 3229 E-mail: sales@gdutil.com

<b>Test item particulars</b> ..... :	
样品信息:	
Cell type..... :	XM6242125
电芯型号	
Nominal Voltage..... :	3.7V
额定电压	
Rated Capacity..... :	4000mAh
额定容量	
Appearance..... :	Orange
颜色	橙色
Number of cell..... :	4pcs (4S1P)
电芯数量	
Dimension(mm)..... :	25.0mm (max) × 44.5mm (max) × 141.0mm(max)
尺寸	
<b>Test case verdicts</b>	
测试判定	
Test case does not apply to the test object..... :	N/A
判定不适用于测试对象	
Test item does meet the requirement..... :	P(Pass)
测试符合规定	
Test item does not meet the requirement..... :	F(Fail)
测试不符合规定	
<b>Testing 测试</b>	
Date of receipt of test item .....	2018-06-15
接样日期	
Date(s) of performance of test..... :	2018-06-15 ~ 2018-07-03
测试周期	
<b>General remarks 备注</b>	
This report shall not be reproduced, except in full, without the written approval of the testing laboratory. 除非全部复制, 未经本实验室书面批准不得部分复制。	
The test results presented in this report relate only to the item tested. 本报告的测试结果仅对送检样品负责。	
"(see remark #)" refers to a remark appended to the report. “(见注#)”指报告的备注。	
Throughout this report a point is used as the decimal separator. 本报告中以点代替小数点。	

**General product information:****产品信息:**

The main features of this model are shown as below:

产品主要信息如下:

Model 型号	Nominal capacity 额定容量	Nominal voltage 额定 电压	Nominal Charge Current 额定充电 电流	Nominal Discharge Current 额定放电 电流	Maximum Charge Current 最大充电 电流	Maximum Discharge Current 最大放电 电流	Maximum Charge Voltage 最大充电 电压	Cut-off Voltage 放电截 止电压
<b>Battery / 电池</b>								
XM6242125	4000mAh	14.8 V	2000mA	800mA	2000mA	4000mA	16.88V	12V
<b>Cell / 电芯</b>								
XM6242125	4000mAh	3.7V	2000mA	2000mA	2000mA	4000mA	4.22V	3.0V

**Test Procedure:****测试程序:**

1. Tests T.1 to T.5 shall be conducted in sequence on the same cell or battery. Tests T.6 and T.8 shall be conducted using not otherwise tested cells. Test T.7 may be conducted using undamaged batteries previously used in Tests T.1 to T.5 for purposes of testing on cycled batteries.

测试T.1-T.5须按顺序依次在同一组电芯或电池上进行。T.6和T.8须用全新的电芯进行测试。T.7可以用之前T.1-T.5测试中完整无损的电池进行测试。

2. In order to quantify the mass loss, the following procedure is provided:

质量损失按照如下公式计算:

$$\text{Mass loss (\%)} = \frac{(M1 - M2)}{M1} \times 100$$

Where M1 is the mass before the test and M2 is the mass after the test. When mass loss does not exceed the values in Table 38.3.1, it shall be considered as "no mass loss".

M1是测试前的重量，M2是测试后的重量。若质量损失不超过Table 38.3.1中的值即可视为“没有质量损失”。

Table 38.3.1 Mass loss limit

Mass M of cell or battery	Mass loss limit
M < 1 g	0.5%
1 g ≤ M ≤ 75 g	0.2%
M > 75 g	0.1%

UN 38.3			
Clause	Requirement + Test	Result - Remark	Verdict
<b>38.3.4.1</b>	<b>Test T.1: Altitude simulation/高度模拟</b>		<b>P</b>
	Test cells and batteries shall be stored at a pressure of 11.6 kPa or less for at least six hours at ambient temperature (20±5°C)/将电芯和电池在温度为20±5°C、大气压力不大于11.6kPa的环境中贮存不少于6个小时。		P
	Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states. /电芯和电池符合要求：无漏液、无排气、无解体、无破裂以及无着火现象；电芯或电池测试后的开路电压不低于测试前开路电压的90%。此项关于电压方面的要求不适用于完全放电后的电芯和电池。	No leakage, no venting, no disassembly, no rupture and no fire. / 无漏液、无排气、无解体、无破裂以及无着火现象。  The data see table 1. / 测试数据见表1。	P
<b>38.3.4.2</b>	<b>Test T.2: Thermal test/温度试验</b>		<b>P</b>
	Test cells and batteries are to be stored for at least six hours at a test temperature equal to 72±2°C, followed by storage for at least six hours at a test temperature equal to - 40±2°C. The maximum time interval between test temperature extremes is 30 minutes. This procedure is to be repeated 10 times, after which all test cells and batteries are to be stored for 24 hours at ambient temperature (20 ±5°C). /首先将样品放在72±2°C的环境中放置至少6个小时，然后放在- 40±2°C的环境中放置至少6个小时。温度转换的最大间隔时间为30分钟。如此循环10次，最后将样品放在20±5°C的环境中静置24小时。		P
	For large cells and batteries the duration of exposure to the test temperature extremes should be at least 12 hours. /对于大电芯和大电池，在高温和低温中放置的时间最少12个小时。		N/A

UN 38.3			
Clause	Requirement + Test	Result - Remark	Verdict
	<p>Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.</p> <p>/电芯和电池符合要求：无漏液、无排气、无解体、无破裂以及无着火现象；电芯或电池测试后的开路电压不低于测试前开路电压的90%。此项关于电压方面的要求不适用于完全放电后的电芯和电池。</p>	<p>No leakage, no venting, no disassembly, no rupture and no fire. / 无漏液、无排气、无解体、无破裂以及无着火现象。</p> <p>The data see table 1. / 测试数据见表1。</p>	P
<b>38.3.4.3</b>	<b>Test T.3: Vibration/振动</b>		<b>P</b>
	<p>Cells and batteries are firmly secured to the platform of the vibration machine without distorting the cells in such a manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal waveform with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting positions of the cell. One of the directions of vibration must be perpendicular to the terminal face. /样品必须牢固地安装在振动台台面上。振动以正弦波形式，以7Hz增加至200Hz，然后减少回到7Hz为一个循环，一个循环持续15分钟的对数前移传送。对样品从三个互相垂直的方向上循环12次，每个方向3个小时，共9个小时。其中一个振动方向必须是垂直样品的极性平面。</p>		P
	<p>The logarithmic frequency sweep shall differ for cells and batteries with a gross mass of not more than 12 kg (cells and small batteries), and for batteries with a gross mass of more than 12 kg (large batteries). /对于质量不大于12kg的样品(电芯和小电池)和质量超过12kg的电池(大电池)，对数扫频不同，</p>		P
	<p>For cells and small batteries: from 7 Hz a peak acceleration of 1 gn is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 8 gn occurs (approximately 50 Hz). A peak acceleration of 8 gn is then maintained until the frequency is increased to 200 Hz. /对于电芯和小电池，对数扫频为：从7Hz开始保持1gn的最大加速度直到频率为18Hz，然后将振幅保持在0.8mm (总偏移1.6mm) 并增加频率直到最大加速度达到8gn (频率约为50Hz)，将最大加速度保持在8gn直到频率增加到200Hz。</p>		P

GUANGDONG UTL CO., LTD.

Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China

Tel:+86-769-3893 3228 Fax:+86-769-3893 3229 E-mail: sales@gdutil.com

UN 38.3			
Clause	Requirement + Test	Result - Remark	Verdict
	For large batteries: from 7 Hz to a peak acceleration of 1 gn is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 2 gn occurs (approximately 25 Hz). A peak acceleration of 2 gn is then maintained until the frequency is increased to 200 Hz. /对于大电池, 对数扫频为: 从7Hz开始保持1gn的最大加速度直到频率为18Hz, 然后将振幅保持在0.8mm (总偏移1.6mm) 并增加频率直到最大加速度达到2gn (频率约为25Hz), 将最大加速度保持在2gn直到频率增加到200Hz。		N/A
	Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire during the test and after the test and if the open circuit voltage of each test cell or battery directly after testing in its third perpendicular mounting position is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states. /电芯和电池符合要求: 无漏液、无排气、无解体、无破裂以及无着火现象; 电芯或电池测试后的开路电压不低于测试前开路电压的90%。此项关于电压方面的要求不适用于完全放电后的电芯和电池。	No leakage, no venting, no disassembly, no rupture and no fire. / 无漏液、无排气、无解体、无破裂以及无着火现象。 The data see table 1. / 测试数据见表1。	P
<b>38.3.4.4</b>	<b>Test T.4: Shock/冲击</b>		<b>P</b>
	Test cells and batteries shall be secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery. /以稳固的托架固定住每个样品。		P
	Shock: a half-sine shock of peak acceleration of 150 gn (or Acceleration( $g_n$ )= $\sqrt{\frac{100850}{mass}}$ , which is smaller) and pulse duration of 6 milliseconds, large cells and large batteries shall be subjected to a half-sine or peak acceleration of 50 gn (or Acceleration( $g_n$ )= $\sqrt{\frac{30000}{mass}}$ , which is smaller) and pulse duration of 11 milliseconds/对小电芯或小电池以峰值为150 gn (或与 $\sqrt{\frac{100850}{mass}}$ 中的较小值) 的半正弦的加速度撞击, 脉冲持续6毫秒, 大电芯和大电池组须经受最大加速度50 gn (或与 $\sqrt{\frac{30000}{mass}}$ 中的较小值) 和脉冲持续时间11毫秒的半正弦波冲击。		P

GUANGDONG UTL CO., LTD.

Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China

Tel:+86-769-3893 3228 Fax:+86-769-3893 3229 E-mail: sales@gdutil.com

<b>UN 38.3</b>			
Clause	Requirement + Test	Result - Remark	Verdict
	Each cell or battery shall be subjected to three shocks in the positive direction and to three shocks in the negative direction in each of three mutually perpendicular mounting positions of the cell or battery for a total of 18 shocks. /每个样品必须在三个互相垂直的电池安装方位的正方向经受三次冲击，接着在反方向经受三次冲击，总共经受18次冲击。		P
	Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states. /电芯和电池符合要求：无漏液、无排气、无解体、无破裂以及无着火现象；电芯或电池测试后的开路电压不低于测试前开路电压的90%。此项关于电压方面的要求不适用于完全放电后的电芯和电池。	No leakage, no venting, no disassembly, no rupture and no fire. / 无漏液、无排气、无解体、无破裂以及无着火现象。  The data see table 1. / 测试数据见表1。	P
<b>38.3.4.5</b>	<b>Test T.5: External short circuit/外部短路</b>		<b>P</b>
	The cell or battery to be tested shall be temperature stabilized so that its external case temperature reaches $57\pm 4^{\circ}\text{C}$ . /保持测试环境温度稳定在 $57\pm 4^{\circ}\text{C}$ ，以便样品外表温度达到 $57\pm 4^{\circ}\text{C}$ 。		P
	The cell or battery at $57 \pm 4^{\circ}\text{C}$ shall be subjected to one short circuit condition with a total external resistance of less than 0.1 ohm. This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to $57\pm 4^{\circ}\text{C}$ , or in the case of the large batteries, has decreased by half of the maximum temperature increase observed during the test and remains below that value. /在环境温度 $57\pm 4^{\circ}\text{C}$ 的条件下，将样品正负极用小于0.1欧姆的总电阻回路进行短路，样品的外表温度恢复到 $57\pm 4^{\circ}\text{C}$ 之后保持短路状态1小时以上；对于大电池，电池温度降低至最高温升值的一半时实验结束。		P
	Cells and batteries meet this requirement if their external temperature does not exceed $170^{\circ}\text{C}$ and there is no disassembly, no rupture and no fire during the test and within six hours after the test./电芯和电池符合要求：在测试过程中以及之后6个小时内，外表温度不超过 $170^{\circ}\text{C}$ ，并且无解体、无破裂和无着火现象发生。	No disassembly, no rupture and no fire. / 无解体、无破裂以及无着火现象发生。  The data see table 1. / 测试数据见表1。	P
<b>38.3.4.6</b>	<b>Test T.6: Impact / Crush/撞击/挤压</b>		<b>P</b>



UN 38.3			
Clause	Requirement + Test	Result - Remark	Verdict
	Test procedure – Impact (applicable to cylindrical cells not less than 18 mm in diameter) /撞击(适合于直径不小于18mm的圆柱形电芯)	Pouch cell/袋状电芯	N/A
	The sample cell or component cell is to be placed on a flat smooth surface. A 15.8 mm±0.1mm diameter, at least 6 cm long, or the longest dimension of the cell, whichever is greater, Type 316 stainless steel bar is to be placed across the centre of the sample. A 9.1 kg±0.1 kg mass is to be dropped from a height of 61±2.5 cm at the intersection of the bar and sample in a controlled manner using a near frictionless, vertical sliding track or channel with minimal drag on the falling mass. The vertical track or channel used to guide the falling mass shall be oriented 90 degrees from the horizontal supporting surface. /将样品放在一个平坦的光滑平面上。将一直径为15.8 mm± 0.1mm, 长度不小于6cm的316不锈钢棒横过样品中部放置后, 将一质量为9.1 kg±0.1 kg的重物从61±2.5 cm的高度落向样品。		N/A
	The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8 mm±0.1mm diameter curved surface lying across the centre of the test sample. Each sample is to be subjected to only a single impact. /接受撞击的样品, 纵轴应与平坦的表面平行并与横放在样品中心的直径15.8 mm±0.1mm弯曲表面的纵轴垂直。每一个样品只接受一次撞击。		N/A
	Test Procedure – Crush (applicable to prismatic, pouch, coin/button cells and cylindrical cells less than 18 mm in diameter). /挤压 (适用于棱柱形、袋状、硬币/纽扣电芯和直径小于18mm的圆柱形电芯)	Pouch cell/袋状电芯	P
	A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5 cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached. /将样品放在两个平面之间挤压, 挤压力度逐渐加大, 在第一个接触点上的速度大约为1.5cm/s。挤压持续进行, 直到出现以下三种情况之一		P
	(a) The applied force reaches 13 kN±0.78 kN; /施加力达到13 kN±0.78 kN		P
	(b) The voltage of the cell drops by at least 100 mV; /样品的电压下降至少100mV		N/A

GUANGDONG UTL CO., LTD.

Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China

Tel:+86-769-3893 3228 Fax:+86-769-3893 3229 E-mail: sales@gdutil.com

UN 38.3			
Clause	Requirement + Test	Result - Remark	Verdict
	(c) The cell is deformed by 50% or more of its original thickness. /电池变形达原始厚度的50%以上。		N/A
	A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis. /棱柱形或袋状电芯应从最宽的一面施压。纽扣/硬币形电芯应从其平坦表面施压。圆柱形应从与纵轴垂直的方向施压。		P
	Each test cell or component cell is to be subjected to one crush only. The test sample shall be observed for a further 6 h. The test shall be conducted using test cells or component cells that have not previously been subjected to other tests. /每个样品都是全新样品，并且只经受一次施压。施压结束后样品应静置观察6小时。		P
	Cells and component cells meet this requirement if their external temperature does not exceed 170°C and there is no disassembly and no fire during the test and within six hours after this test. /电芯满足要求：在测试过程中以及之后6个小时内，外表温度不超过170°C，并且无解体和无着火现象发生。	No disassembly and no fire. /无解体，无着火现象发生。 The data see table 2. /测试数据见表2。	P
<b>38.3.4.7</b>	<b>Test T.7: Overcharge/过充电</b>		<b>P</b>
	The charge current shall be twice the manufacturer's recommended maximum continuous charge current. Tests are to be conducted at ambient temperature. The duration of the test shall be 24 hours. The minimum voltage of the test shall be as follows: /在室温下，以2倍的制造商宣称的最大持续充电电流对样品充电，测试时间为24小时。测试的最小电压如下：		P
	(a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. /如果制造商宣称的充电电压不超过18V，本测试的最小充电电压应是制造商宣称的最大充电电压的两倍或者是22V之中的较小者。	The voltage of the test is 22V, and the current is 4000mA. /测试电压为22V，电流为4000mA.	P
	(b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. /如果制造商宣称的充电电压超过18V，本测试的最小充电电压应该是制造商宣称的最大充电电压的1.2倍。		N/A

GUANGDONG UTL CO., LTD.

Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China

Tel:+86-769-3893 3228 Fax:+86-769-3893 3229 E-mail: sales@gdutil.com

<b>UN 38.3</b>			
Clause	Requirement + Test	Result - Remark	Verdict
	There is no disassembly and no fire during the test and within seven days after the test. /在测试中和测试完成后7天内，样品无解体和无着火现象。	No disassembly and no fire. /无解体，无着火现象发生。 The data see table 3./测试数据见表3。	<b>P</b>
<b>38.3.4.8</b>	<b>Test T.8: Forced discharge/强制放电</b>		<b>P</b>
	Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12V D.C. power supply at an initial current equal to the maximum discharge current specified by the manufacturer. /在室温下，将单个电芯连接在12V的直流电源上进行强制放电，此直流电源供给每个电芯初始电流为制造商宣称的最大放电电流。 The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell shall be forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere). /指定的放电电流通过串联在测试电芯上的合适大小和功率的负载来获得，每个电芯的强制放电时间(小时)为额定容量除以初始电流(安培)。		<b>P</b>
	There is no disassembly and no fire during the test and within seven days after the test. /在测试中和测试完成后7天内，样品无解体和无着火现象发生。	No disassembly and no fire. /无解体和无着火现象发生。 The data see table 4. /测试数据见表4。	<b>P</b>

## Tables

Table 1: T.1~T.5 / 表1. 测试 1~测试 5											
Sample No. 样品编号	Mass prior to test (g)/测试前质量	OCV prior to test (V)/测试前开路电压	Test 1: Altitude simulation/ 测试 1: 高度模拟		Test 2: Thermal test/ 测试 2: 温度试验		Test 3: Vibration/ 测试 3: 振动		Test 4: Shock/ 测试 4: 冲击		Test 5: External Short Circuit/ 测试 5: 外部短路
			Mass loss 质量损失(%)	Change ratio 电压比(%)	Mass loss 质量损失(%)	Change ratio 电压比(%)	Mass loss 质量损失(%)	Change ratio 电压比(%)	Mass loss 质量损失(%)	Change ratio 电压比(%)	Temp. (°C) 温度(°C)
b1#	242.752	16.794	0.000	99.988	0.001	99.899	0.000	99.988	0.000	99.994	57.2
b2#	242.480	16.792	0.000	99.994	0.001	99.929	0.000	99.994	0.000	99.994	57.2
b3#	242.439	16.790	0.001	99.994	0.001	99.934	0.000	99.994	0.000	99.994	57.3
b4#	242.287	16.789	0.000	99.994	0.001	99.911	0.000	99.988	0.000	99.988	57.5
b5#	242.925	16.793	0.001	99.988	0.002	99.917	0.000	99.994	0.001	99.988	57.6
b6#	242.987	16.796	0.000	99.988	0.001	99.905	0.001	99.994	0.000	99.994	57.4
b7#	242.740	16.793	0.001	99.994	0.001	99.911	0.000	99.988	0.000	99.994	57.3
b8#	243.187	16.794	0.000	99.988	0.001	99.917	0.000	99.988	0.000	99.994	57.5

GUANGDONG UTL CO., LTD.

Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China

Tel:+86-769-3893 3228 Fax:+86-769-3893 3229 E-mail: sales@gdutl.com

## Tables

Table 2: Crush/ 表2: 挤压						
Test 6: Crush 测试6: 挤压	Sample No. 样品编号	c1#	c2#	c3#	c4#	c5#
	OCV prior to test/ 测试前开路电压(V)	3.871	3.865	3.847	3.862	3.875
	Temp. (°C) 温度(°C)	23.3	23.6	23.4	23.6	23.3

Table 3 : Overcharge / 表3: 过充电									
Test 7: Overcharge 测试7: 过充 电	Sample No. 样品编号	b1#	b2#	b3#	b4#	b5#	b6#	b7#	b8#
	OCV prior to test/ 测试前开路电压(V)	16.790	16.792	16.796	16.791	16.794	16.793	16.792	16.794

Table 4 : Forced discharge / 表4: 强制放电											
Test 8: Forced discharge 测试8: 强制 放电	Sample No. 样品编号	c6#	c7#	c8#	c9#	c 10#	c11#	c12#	c 13#	c14#	c15#
	OCV prior to test/ 测试前开路电压(V)	3.233	3.217	3.292	3.260	3.310	3.251	3.219	3.288	3.228	3.204
	Sample No. 样品编号	c16#	c17#	c18#	c19#	c20#	c21#	c22#	c23#	c24#	c25#
	OCV prior to test/ 测试前开路电压(V)	3.214	3.349	3.202	3.230	3.263	3.286	3.244	3.319	3.196	3.332

Photos



Figure 1 Top view of Battery



Figure 2 Bottom view of Battery

Photos




Figure 3 Top view of cell




Figure 4 Bottom view of cell